



Preparation, Crystal Structure, Thermal Properties and Vibrational Modes of Tl_2CdI_4 Nanocomposite Material

Noorus Saba*, Afaq Ahmad

Solid State Chemistry Lab, Department of Chemistry, Aligarh Muslim University, Aligarh - 202002, UP, India.

ARTICLE DETAILS

Article history:

Received 20 March 2016

Accepted 09 May 2016

Available online 09 July 2016

Keywords:

Fast Ion Conductor

X-Ray Powder Diffraction

Thermal Analysis

ABSTRACT

The new compound Tl_2CdI_4 has been prepared and characterized by IR spectroscopy, powder X-ray diffraction, thermal analysis, far IR spectroscopy. The compounds Tl_2CdI_4 for which phase diagrams are available in the literature were characterized by IR spectroscopy and their identities were confirmed by far-IR spectroscopy, X-ray powder diffraction and thermal analysis. Tl_2CdI_4 , undergoes a sharp order-disorder phase transition at elevated temperatures that can be detected by the measurement of IR spectra as a function of temperature. This work suggests that thallium (I) ionic conductors may exist, analogous to some well-known double salt conductors based on simple silver (I) and copper (I) halides. In addition, the present study demonstrates the usefulness of IR spectroscopy in the characterization of heavy metal ionic conductors. The mobility of Tl^+ in halide compounds has been investigated to develop an understanding of the factors which are important in fast ion conduction. These compounds are characterized by transitions at elevated temperatures to disordered phases in which the M ion is highly mobile. Trends in the transition temperatures, conductivities, and activation energies for ion transport demonstrate that Tl^+ are less mobile than Cu^+ and Ag^+ . The crystal structure of the low-temperature phase of Tl_2CdI_4 has been determined at 160 °C. The material crystallizes with two formula units in space group $C2_2-P2_1$ of the monoclinic system in a cell of dimensions $a = 7.661 \text{ \AA}$, $b = 7.971 \text{ \AA}$, $c = 10.074 \text{ \AA}$, $\beta = 118.39^\circ$. The Cd^{2+} ions are tetrahedrally coordinated by I^- ions. The Tl^+ ions are found to reside in seven-coordinate sites approximating C_{2v} , capped trigonal prisms. There is no clear-cut migration path for the Tl^+ ions, but some plausible conduction mechanisms are discussed.

1. Introduction

A large number of papers appeared on isomorphous series constituting A_2MX_4 composition. These salts are known to undergo a successive phase transformation characterized by IC-C features described in [1].

Fast ion conductors, where a single ionic species diffuses in an otherwise static matrix, have been intensively researched since the middle of the last century. These materials are of practical interest since they hold the promise of enabling all solid state electrochemical devices such as high energy density rechargeable batteries [2–4] and solid state electrochemical conductors. A_2MX_4 compounds (where $A = Tl, Ag, Cu, M = Cd, Hg, Zn, X = Cl, Br, I$ etc.), belong to a class of fast-ionic solids which are promising materials for use in solid state batteries and fuel cells due to extraordinarily high ionic conductivity at supercritical temperatures [5]. In such ternary fast-ionic conductors mobile ions of different type contribute to the total electric conductivity and thus result in different vibration frequencies. In their turn, the vibration frequencies reflect the interaction between the lattice and charge carriers. Although the lattice dynamics of A_2MX_4 family representatives was extensively studied [6, 7]. Results obtained for Tl_2HgI_4 , Tl_2CdI_4 are extremely scarce in the literature. Therefore Tl_2HgI_4 and Tl_2CdI_4 remains the only compound in the A_2MX_4 family for which complete information describing the material properties. Motivated by this situation, in our study we make use the mentioned above Tl_2HgI_4 , Tl_2CdI_4 as a ternary derivative of the “classic” solid electrolyte, TlI , is an interesting model material to study by combining theoretical and experimental techniques from methodological considerations as well. Thallium batteries or microbatteries can be attractive as power sources for some classes of portable electronic devices operating near room temperature, which may serve as electrolytes in such batteries. Thallium ion conducting composites are interesting materials specially to develop solid-state electrochemical devices such as batteries, fuel cells, sensors,

supercapacitors, electrochromic display devices, etc. Therefore, in the present study, the investigations are focused on the following alternative novel composite thallium fast ion conductors. In the $[Tl_2MI_4]$ (where $M = Cd$) systems, $[Tl_2MI_4]$ are pure materials, It has been observed that a much better solid electrolyte composite system can be prepared as $[Tl_2CdI_4]$ [8].

2. Experimental Methods

2.1 Materials

The following materials were used as received; TlI and CdI_2 obtained from HIMEDIA and LOBA CHEMIE (India), with stated purity 99.99% of 99% respectively.

2.2 Preparation of Composite Fast Ion Conductors $[Tl_2CdI_4]$

Thallium tetra iodo cadmate $[Tl_2CdI_4]$ was prepared from TlI and CdI_2 by the solid state reactions method. TlI and CdI_2 were mixed in the requisite composition (according to Eq. 1) in an Agate mortar and were heated at 115 °C (388 K) for 5 days (120 h) in an air oven (CE 0434 NSW- 144), in silica crucible with intermittent grinding. The rate of heating was initially kept at 50 °C per hours for 12 hours. After cooling, the dark lemony color compound changed to light yellow color. Tl_2CdI_4 is dark lemony color above 115 °C. The color transition from light yellow to dark lemony occurred at 115 °C and decomposes above 150 °C. The resulting material at room temperature was used for further studies [9].



2.3 Characterization of Composite Fast Ion Conductors $[Tl_2CdI_4]$

The novel fast ion conductors $[Tl_2CdI_4]$, were prepared and investigated by X-ray powder diffraction, Fourier Transmission (far-IR and mid-IR region) spectral analysis, Differential thermal analysis (DTA), Differential scanning calorimetry (DSC) and Thermogravimetric analysis (TGA) to confirmed the formation of all the fast ion conductors.

*Corresponding Author

Email Address: sabaamu@gmail.com (Noorus Saba)

2.3.1 X-Ray Powder Diffraction Studies

X-ray powder diffraction were performed for the systems $[\text{Tl}_2\text{CdI}_4]$, after the reaction was completed using Rigaku Rad B powder diffractometer and a Bruker AXS D8 Advance diffractometer with a K-beta filter with $\text{Cu-K}\alpha$ ($\lambda = 1.54060 \text{ \AA}$) radiation at room temperature. The angle range for measurement was from $10\text{-}70^\circ$ and the scanning speed was 1° min^{-1} . The x-ray diffractogram values of the samples $[\text{Tl}_2\text{CdI}_4]$ correspond to standard values of $[\text{Tl}_2\text{CdI}_4]$ from the literature confirms the formation of compounds.

2.3.2 Far-IR Spectral Analysis

The Far-IR spectrum was recorder for fast ionic conductor $[\text{Tl}_2\text{CdI}_4]$ in the far-infrared range $30\text{-}400 \text{ cm}^{-1}$ at room temperature using a Perkin Elmer/FTIR Spectrometer measured in KBr. The far-infrared spectral region is the range of wavenumbers where one finds many of the large-amplitude anharmonic vibrations. These include both the symmetric and asymmetric internal torsional modes of many small organic and organometallic molecules.

2.3.3 FTIR Measurements

The FTIR spectrum was recorder for the fast ionic conductor $[\text{Tl}_2\text{CdI}_4]$ in the mid-infrared range $400\text{-}4000 \text{ cm}^{-1}$ ($25\text{-}25 \mu\text{m}$) at room temperature using a INTERSPEC-2020, FTIR spectrophotometer measured in KBr. Mid-infrared spectra used to study the fundamental vibrations and associated rotational-vibrational structures.

2.3.4 Thermal Analysis

Differential thermal analysis (DTA), Differential scanning calorimetry (DSC) and Thermo-gravimetric analysis (TGA) was carried out on $[\text{Tl}_2\text{CdI}_4]$ mixed composite samples, using DTG-60H thermal analyser in nitrogen atmosphere with flow rate of 30 mLmin^{-1} and heating rate $25^\circ \text{ Cmin}^{-1}$ in the temperature range $20\text{-}500^\circ \text{ C}$. The reference used was 10 mg alumina powder.

3. Results and Discussion

3.1 FTIR Analysis

3.1.1 Far-IR Discussion in $[\text{Tl}_2\text{CdI}_4]$

The IR spectrum of the vapour over solid Tl_2CdI_4 was studied in the $30\text{-}700 \text{ cm}^{-1}$ region at room temperature are shown in Fig. 1. The infrared spectrum of Tl_2CdI_4 solid at room temp showed two distinct absorption bands. The absorption around 103.03 cm^{-1} shows typical PR band structure of a diatomic molecule and is assigned to the fundamental Tl-I stretching frequency of the monomer. For the band origin at 73.35 cm^{-1} can be attributed to the $(\text{TlI})_2$ dimeric molecule [10]. IR- measurements shows that a significant amount of dimeric molecules is present in the vapour over TlI (I) at the temperature of the present experiments. Ionic model calculations based on Rittners electrostatic model [11] predicted a square planar structure (D_{2h} symmetry) as the most stable arrangement for $(\text{TlI})_2$. This structure allows three of the total six normal modes of vibration to be IR active. The B_{2u} and B_{3v} stretching modes involve high frequency in plane motion and the B_{1u} bending mode lower frequency out of plane motion. On the basis of these consideration the peak at 73.35 cm^{-1} is due to the stretching motion and the peak at ca 43.35 cm^{-1} to the bending motion of the $(\text{TlI})_2$ molecule. There is however, no clear argument for the assignment of the observed stretching band to the B_{2u} and B_{3v} mode [11].

The spectrum of Tl_2CdI_4 solid consisted of two strong absorption bands are listed in Table 1. It is concluded that both peaks are due to CdI_2 molecular species. The linear structure of the CdI_2 molecule ($D_{\infty h}$ symmetry), as established by electron diffraction measurements [12-14], allow two of the total of three fundamental frequencies to be infrared active and consequently, the assignment is straight forward, the symmetric Cd-I stretching frequency ν_3 at 232.45 cm^{-1} and I-Cd-I blending frequency ν_2 at 141.76 cm^{-1} . The additional sharp lines in the spectrum are due to the rotational spectrum of H_2O impurities. The IR spectrum of Tl_2CdI_4 solid, also shows three distinct absorption bands at 319.70 , 436.1 and 467.64 cm^{-1} . On further increasing the wavenumber the position of the absorption bands are in excellent agreement with those of the Tl_2CdI_4 molecules [15] above 400 cm^{-1} , the intensity of the peaks decreases, owing to condensation of CdI_2 in the colder parts of the optical cell, these bands corresponds to those TlI and indicate the presence of TlI and $(\text{CdI}_2)_2$ molecules. In addition, numerous sharp absorption bands of the rotational spectrum of H_2O were presents, which were partially removed by spectral subtraction. The present results show that the successive release of CdI_2 and TlI/ $(\text{CdI}_2)_2$ vapour species occurs during heating, pointing towards

dissociation of Tl_2CdI_4 molecules under the conditions of the experiments. Additional peaks that might indicate the presence of Tl-Cd-I species have been observed.

Table 1 Far-IR bands in Tl_2CdI_4 and assignments

Compound	Value (cm^{-1})	Assignment	Nature
TlI	103.03	ω_e	TlI stretch of the monomer
	73.35	ν_5	Asymmetric Cd-I stretch of the dimer
CdI ₂	43.35	-	-
	232.45	ν_3	Asymmetric Cd-I stretch
	141.76	ν_2	I-Cd-I blend
Tl_2CdI_4	319.70	-	Dissociation of Tl_2CdI_4 molecule
	436.1	-	TlI - stretch
	467.64	-	$(\text{CdI}_2)_2$ -stretch




Fig. 1 Far-IR spectrum for $[\text{Tl}_2\text{CdI}_4]$ fast ionic conductors

3.1.2 FTIR Discussion in Tl_2CdI_4

Assuming the β -phase is tetragonal, the number and symmetry of normal modes can be determined. Group theory analysis finds the following number and symmetries for the 10 optical modes in Tl_2CdI_4 materials.

$$\text{Tl}_2\text{CdI}_4: 3A + 5B + 5E$$

The Infrared and Raman selection rules give the following allowed mode symmetries.

$$\begin{array}{ll} \text{Infrared} & \text{Tl}_2\text{CdI}_4: 5B + 5E \text{ (10 Bands)} \\ \text{Raman} & 3A + 5B + 5E \text{ (13 Bands)} \end{array}$$

Using projection operators, we find that the B symmetry mode involve motion of the cation along the tetragonal c axis (z), and the E modes involve motion of the cations, along the a and b axes (x or y), B mode couple to electric fields along the z axis and E modes couple to fields in the xy plane, so that FTIR spectra would determine the mode-symmetry assignments uniquely [16-19].

3.1.3 Factor Group Analysis of Tl_2CdI_4

The irreducible representation for the 10 IR allowed modes are listed in Table 2. The unit cell group analysis of Tl_2CdI_4 is also shown in Table 2 [18], with the $D_{2d} - S_4$ correlation being A_1 and A_2 to A, B and B_2 to B and E to E. Fig. 2 shows FTIR spectrum for $[\text{Tl}_2\text{CdI}_4]$ fast ionic conductors. In the IR spectra of $[\text{Tl}_2\text{CdI}_4]$ the 2925.26 cm^{-1} peak in Table 2 is strongest in xx, yy and zz direction making it an A. The peak at 1609.26 cm^{-1} and 1740.64 cm^{-1} are strongest in the xx and yy polarizations and therefore belongs to A or B classes. The only noticeable peaks in xz polarization and E symmetry is at 461.59 cm^{-1} and the 859.31 cm^{-1} shoulder appears to be weak in xx, zz and xz polarization making it likely that at least some of the peaks causing this feature would be maximized in the xy polarization and therefore of B symmetry in $[\text{Tl}_2\text{CdI}_4]$.

Unassigned and a speculatively assignment for the 753.57 cm^{-1} feature. CdI_2 contamination peaks also found in at 510.10 cm^{-1} for $[\text{Tl}_2\text{CdI}_4]$. Peaks of B and E symmetry are allowed in the IR spectra and should be strong peaks. The occurrence of 510.10 cm^{-1} for $[\text{Tl}_2\text{CdI}_4]$ in the IR strengthens the E assignment for the peak at 461.59 cm^{-1} (Table 2).

Table 2 $[\text{Tl}_2\text{CdI}_4]$ fast ionic conductors room temperature peaks and assignments

Tl_2CdI_4 (cm^{-1})	Assignments
2925.26	A $(\text{CdI}_4)^{-2}$ symmetric stretch respectively
1535.06	Tl-I and Cd-I symmetric stretch
1609.26	A $(\text{CdI}_4)^{-2}$ deformation, M-I stretching
859.31	? Deformation
1740.64	B
461.59	E Tl ⁺ attempt frequency




Fig. 2 FTIR spectrum for $[Tl_2CdI_4]$ fast ionic conductors

Table 3 $[Tl_2CdI_4]$ fast ionic conductors room temperature peaks and assignments

$[Tl_2CdI_4]$	Symmetry	Assignment
2925.26	A	CdI_4^{2-} Symmetric stretch
1609.26	A	CdI_4^{2-} deformation, M-I stretching
859.31	?	deformation
1740.64	B	Tl-I, Ag-I symmetric stretch
461.59	B	Tl ⁺ attempt frequency

3.1.4 FTIR Comparison in Tl_2CdI_4

From Table 3, the vibrational modes can be assigned by considering Tl_2CdI_4 as consisting of the vibrational modes of TlI and $(CdI_4)^{2-}$ species. In fact, as shown in Fig. 2, almost all the bands due to TlI and $(CdI_4)^{2-}$ are seen in the pure Tl_2CdI_4 composites. The band at 1609 cm^{-1} can be assigned to the symmetric stretching "A" mode of $(CdI_4)^{2-}$ species and this band is the strongest band at room temperature [20]. This assignment is in good agreement with the other $(CdI_4)^{2-}$ tetrahedral compounds [21]. On the doping of $(TlI:CdI_2)$ ions, the pure Tl_2CdI_4 , all six bands shifted to 461.59, 510.10, 753.37, 859.31, 1031.21 and 1350.96 cm^{-1} . The 1000-1500 cm^{-1} region consists of two bands at the positions 1398.71 cm^{-1} and 1535.08 cm^{-1} at room temperature and at low temperature, these bands are expected to split.

It is known from the IR spectra of Tl_2CdI_4 -ions conductors that this region consists of Tl-I [22] stretching modes. Hence, in all $[Tl_2CdI_4]$ composite samples, also the bands in this region can be assigned to symmetric stretching modes of Tl-I. Below 700 cm^{-1} , there are two sharp bands at 461.59 and 510.10 cm^{-1} in pure Tl_2CdI_4 [20], it is known from factor group analysis studies [18] that the bands in this region are due to deformation type metal-iodine vibrations. On comparison with $(CdI_4)^{2-}$ species vibrations, the bands at 461.59 and 510.10 cm^{-1} in pure Tl_2CdI_4 , can be assigned to Cd-I deformation type bands. The band at 461.59 cm^{-1} in pure Tl_2CdI_4 , is attributed to the E symmetry of Tl⁺ translational mode and is the characteristic attempt frequency of Tl⁺ ion arising from the diffusive behaviour to oscillatory behaviour. This assignment is well explained by Shriver [19] by referring to the negative pressure dependence and also using theoretical calculations. The value assigned to the attempt frequencies in Tl_2CdI_4 is similar to cation transition modes [19, 20]. Another possibility is that motion of very large amplitude (diffusive like) is able to create configurational disorder which allows all IR modes [23].

Inspection of Table 3 and Fig. 2, shows that IR spectra of $[Tl_2CdI_4]$ conductors exhibit the strongest feature at ca 1609.19 cm^{-1} , while the infrared activity below 900 cm^{-1} is weak. On the basis of the above discussion, these results strongly suggest that the existence of $(CdI_4)^{2-}/(Tl^+)$ tetrahedral in Tl_2CdI_4 ionic conductors should be excluded at least in concentration detectable by infrared spectroscopy [20].

3.2 X-Ray Diffraction

Room temp XRD patterns obtained for $[Tl_2CdI_4]$ sample are shown in Fig. 3. It is interesting to note from Fig. 3 that three prominent diffraction peaks, which appears at $2\theta = 24.8^\circ$, 41.1° , and 48.6° respectively, in the case of $[Tl_2CdI_4]$ may be attributed to the presence of TlI. The occurrence of XRD peaks around $2\theta = 22^\circ$, 24° and 39.38° reveals the presence of CdI_2 in the samples [24]. Further the appearance of peak around $2\theta = 38^\circ$, 44° , and 65° indicates the presence of Tl in $[Tl_2CdI_4]$ specimen. The occurrence of XRD peaks at $2\theta = 36^\circ$, 38.8° , and 68° indicates the presence of Cd-I in the samples. It is also evident from fig 3 that the occurrence of peaks around $2\theta = 29^\circ$ and 45° shows the presence of $(CdI_4)_2$ also the appearance of peaks at $2\theta = 30.2^\circ$ and 31° reveals the presence of Tl-Cd-I.

A careful analysis of the XRD patterns obtained for $[Tl_2CdI_4]$ has indicated the presence of several phases including TlI, Tl, CdI, $(CdI_4)_2$, Tl-Cd-I in the sample, the formation of two main products $(CdI_4)_2$ and Tl-Cd-I is apparently due to the possible solid state reactions occurring within the sample [24].




Fig. 3 X-ray diffractogram for $[Tl_2CdI_4]$ fast ionic conductors

3.3 Thermal Analysis

3.3.1 Differential Scanning Calorimetry (DSC)

Fig. 4 depicts the DSC thermograms recorded for $[Tl_2CdI_4]$ sample were found to exhibit certain interesting features. DSC curves obtained for the $[Tl_2CdI_4]$ exhibited endothermic peaks at 265.60 $^\circ C$. The above mentioned endothermic peaks are comparable to that of $\beta \rightarrow \alpha$ phase transition of pure TlI ($\approx 260^\circ C$). The DSC results therefore suggest that the combination of two starting materials namely TlI and CdI_2 is complete, resulting in the formation of new substances $[Tl_2CdI_4]$ which are probably Tl⁺ ion conductors having very small traces of TlI. The absence of TlI diffraction peaks in the typical XRD patterns for the $[Tl_2CdI_4]$ may be attributed to the fact that TlI content in this particular compound is very insignificant and that it could not effect any appreciable change in the observed XRD patterns [25].




Fig. 4 DSC for $[Tl_2CdI_4]$ fast ionic conductors




Fig. 5 DTA, TGA for $[Tl_2CdI_4]$ fast ionic conductors

3.3.2 Differential Thermal Analysis (DTA)

DTA curves for pure Tl_2CdI_4 sample is shown in Fig. 5. Endothermic peaks observed during the DTA analysis carried out for $[Tl_2CdI_4]$ of the ternary system are shown in Table 4. The transition temperature values, which are comparable to that of $\beta \rightarrow \alpha$ phase transition temperature of pure AgI (≈ 420 K), tend to indicate the presence of TlI in these $[Tl_2CdI_4]$ specimen as one of their constituents. This feature is found to be in good agreement with that obtained from the present XRD analysis in view of the fact that the latter confirmed the presence of TlI in $[Tl_2CdI_4]$. Thus the present structural and thermal features are found to be in conformity with each other [26].

Table 4 X-ray diffractogram peaks and assignment for $[\text{Ti}_2\text{CdI}_4]$ fast ion conductors

2 θ	Peak Assignment
24.8°	TII
41.1°	
48.6°	
22°, 24°	CdI ₂
39.38°	
38°	TI
44°	
65°	
36°	Cd-I
38.8°	
68°	
29°	(CdI ₄) ₂
45°	
30.2°	TI-Cd-I
31°	

3.3.3 Thermo-Gravimetric Analysis (TGA)

Fig. 5 indicates that $[\text{Ti}_2\text{CdI}_4]$ is hydrated by the absorption of the atmospheric water. In the TGA analysis of this hydrated sample, the decrease of about 4% in weight with the dehydration was observed as shown in Fig. 4. The composition of hydrated compound kept under the ambient atmosphere was determined to be $[\text{Ti}_2\text{CdI}_4] \cdot 1.5 \text{H}_2\text{O}$ [26].

4. Conclusion

Thus, novel composite fast ion conductors $[\text{Ti}_2\text{CdI}_4]$, were prepared and investigated also by X-ray powder diffraction, FTIR spectral analysis, Differential thermal analysis (DTA), Differential scanning calorimetry (DSC) and Thermogravimetric analysis (TGA) studies to confirm the formation of all the fast ion conductors.

Acknowledgements

The authors are gratefully acknowledged to UGC New Delhi for financial assistance as UGC-PDF Women Scientist Scheme. The authors also thankful to Prof. Reshef Tenne and Dr. Feldmann at the Weizmann Institute of Science (Israel) for obtaining the x-ray measurements of our pure and doped samples. The authors also gratefully acknowledge the Chairman of the Department of Chemistry for providing the research facilities.

References

- [1] O.P. Lamba, M.B. Patel, S. Ram, P. Chand, H.D. Bist, Raman scattering study of the phase sequence in A_2BX_4 halides, *Solid State Commun.* 50 (1984) 321-325.
- [2] J.O. Besenhard, *Handbook of battery materials*, Wiley-VCH, Weinheim, 1999.
- [3] A.L. Laskar, S. Chandra, *Superionic solids and solid electrolytes: Recent trends*, Academic Press, San Diego, 1989.
- [4] H.W. Zandbergen, The crystal structure of α -thallium hexaiodochromate, Tl_4CrI_6 , *Acta Cryst. B.* 35 (1979) 2852-2855.
- [5] C. A. Angell, Mobile ions in amorphous solids, *Annu. Rev. Chem.* 43 (1992) 693-717.
- [6] S. Hull, *Superionics: crystal structures and conduction processes*, *Rep. Prog. Phys.* 67 (2004) 1233-1314.
- [7] J.H. Kennedy, C. Schaupp, Y. Yang, Z. Zhang, Composition and properties of thallium mercury iodide, *J. Solid State Chem.* 88; 1990: 555-563.
- [8] R.C. Agrawal, R. Kumar, A. Chandra, Transport studies on a new fast silver ion conducting system: $0.7[0.75\text{AgI}:0.25\text{AgCl}]:0.3[\text{yAg}_2\text{O}:(1-y)\text{B}_2\text{O}_3]$, *Solid State Ionics* 84 (1996) 51-60.
- [9] K.I. Avdienko, D.V. Badikov, V.V. Badikov, V.I. Chizhikov, V.L. Panyutin, G.S. Shevyrdyaeva, et al, Optical properties of thallium mercury iodide, *Optical Materials*, 23 (2003) 569-573.
- [10] V.P. Glushko, L.V. Gurvich, G.A. Bergman, I.V. Veits, V.A. Medvedev, G.A. Khachkuruzov, V.S. Yungman, *Termodinamicheskie svoista individualnykh veshchestv*, Vol. IV, Nauka, Moscow, 1982.
- [11] B.T. Gowda, S.W. Benson, Structure and energetics of alkali-metal halide dimer molecules, *J. Chem. Soc. Faraday Trans.* 79 (1983) 663-675.
- [12] U. Lauer, J. Maier, Conductivity enhancement and microstructure in AgCl/AgI composites, *Sol. Stat. Ionics* 51 (1992) 209-213.
- [13] H.H. Hofer, W. Eysel, U.V. Alpen, Electrochemistry of Na_2SO_4 (I) solid solutions with aliovalent cation substitution, *Sol. Stat. Chem.* 36 (1981) 365-370.
- [14] A.V. Franiv, O.S. Kushnir, I.S. Girnyk, V.A. Franiv, I. Kityk, M. Piasecki, K.J. Plucinski, Growth, crystal structure, thermal properties and optical anisotropy of Ti_4CdI_6 single crystals, *Ukr. J. Phys. Opt.* 14 (2013) 6-14.
- [15] E. Kartini, T. Sakuma, K. Basar, M. Ihsan, Mixed cation effect on silver–lithium solid electrolyte $(\text{AgI})_{0.5}(\text{LiPO}_3)_{0.5}$, *Sol. Stat. Ionics* 179 (2008) 706-711.
- [16] M. Hassan, M.S. Nawaz, Rafiuddin, Ionic conduction and effect of immobile cation substitution in binary system $(\text{AgI})_{4/5}-(\text{PbI}_2)_{1/5}$, *Radiat. Eff. Defect. S.* 163 (2008) 885-891.
- [17] K. Wakamura, Characteristic properties of dielectric and electronic structures in super ionic conductors, *Solid State Ionics* 149 (2002) 73–80.
- [18] R. Sudharsanan, T.K.K. Srinivasan, Radhakrishna, Raman and far IR studies on Ag_2CdI_4 and Cu_2CdI_4 superionic compounds, *Solid State Ionics* 13 (1984) 277-283.
- [19] A. Viswanathan, S. Austin Suthanthiraraj, Impedance and modulus spectroscopic studies on the fast ion conducting system $\text{CuI}-\text{Ag}_2\text{MoO}_4$, *Solid State Ionics* 62 (1993) 79-83.
- [20] E.A. Secco, A. Sharma, Structure stabilization: locking-in fast cation conductivity phase in TII, *J. Phys. Chem. Sol.* 2 (1995) 251-254.
- [21] J.B. Goodenough, Ceramic solid electrolytes, *Solid State Ionics* 94 (1997) 17-25.
- [22] S. Geller (Ed.), *Solid Electrolytes*, Springer, Berlin, 1977.
- [23] S. Hull, *Superionics: crystal structures and conduction processes*, *Rep. Prog. Phys.* 67 (2004) 1233-1314.
- [24] A. Phukan, J.N. Ganguli, D.K. Dutta, ZnCl_2 - Zn^{2+} -Montmorillonite composite: efficient solid acid catalyst for benzylation of benzene, *J. Mol. Catalyt. A: Chem.* 202 (2003) 279-287.
- [25] A. Viswanathan, S.A. Suthanthiraraj, A study of fast ion transport in the mixed system $\text{CuI}-\text{Ag}_2\text{MoO}_4$, *Solid State Ionics* 58 (1992) 89-96.
- [26] S.A. Suthanthiraraj, R. Mala, Preparation and characterization of fast ionic solid solids in new ternary system $[\text{CuI}-\text{Ag}_2\text{O}-\text{PbO}_2]$, *Solid State Ionics* 144 (2001) 143-149.